

### PRODUCT DESCRIPTION

Stonclad UR is a four-component, trowel applied, polyurethane mortar system. Stonclad UR consists of a urethane-urea binder, pigments, and graded quartz aggregates. Stonclad UR can be applied at thickness ranging from 1/8 in./3 mm to 1/4 in./6 mm depending on application requirements. Stonclad UR is a high impact resistant mortar which exhibits excellent abrasion, thermal shock, thermal cycling and chemical resistant characteristics making it ideal for the food and beverage industry as well as any other applications requiring these properties.

### SYSTEM OPTIONS

#### Cove Base

To provide for an integral seal at the joint between the floor and the wall, cove bases in heights from 2 to 6 in./5 to 15 cm may be specified.

#### Waterproofing

Where the total system must be waterproofed, the use of Stonhard's Stonproof ME7 membrane system with texture #3 broadcast to refusal is required with strict adherence to application instructions.

#### Coatings

The system is designed as an uncoated mortar system. If coatings are desired, two coats of topcoat are required with a sanding step between the coatings.

### PACKAGING

Stonclad UR is packaged in units for easy handling. Each unit consists of:

#### Mortar

- 2 cartons, each containing:
  - 6 foil bags of Isocyanate
  - 6 poly bags of Polyol

12 individual bags of Part C-1 aggregate

#### Pigment

- 1 carton containing:
  - 12 bags of Part C-2 pigment packs powder

### COVERAGE

Each unit of Stonclad UR will cover approximately 200 sq. ft./18.58 sq. m at a nominal thickness of 1/4 in./6 mm.

### STORAGE CONDITIONS

Store all components of Stonclad UR between 60 to 85°F/16 to 30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life is 3 years in the original, unopened container.

### PHYSICAL CHARACTERISTICS

<b>Compressive Strength</b> .....	.5,000 psi
(ASTM C-579)	after 7 days
<b>Tensile Strength</b> .....	1,000 psi
(ASTM C-307)	
<b>Flexural Strength</b> .....	2,000 psi
(ASTM C-580)	
<b>Flexural Modulus of Elasticity</b> .....	1.1 x 10 <sup>6</sup> psi
(ASTM C-580)	
<b>Hardness</b> .....	.80 to 84
(ASTM D-2240, Shore D)	
<b>Impact Resistance</b> .....	>160 in./lbs.
(ASTM D-2794)	
<b>Flammability</b> .....	Class I
(ASTM E-648)	
<b>Thermal Coefficient of Linear Expansion</b> .....	1.3 x 10 <sup>-5</sup> in./in.°F
(ASTM C-531)	
<b>Water Absorption</b> .....	< 1%
(ASTM C-413)	
<b>VOC Content</b> .....	.5 g/l
(ASTM D-2369, Method E)	
<b>Cure Rate</b> .....	.8 hours for foot traffic
(@ 77°F/25°C)	24 hours for normal operations

**Note:** The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab made test coupons.

### SUBSTRATE

Stonclad UR, with the appropriate primer, is suitable for application over concrete, wood, brick, quarry tile, metal or Stonhard Stonset grouts. For questions regarding other possible substrates or an appropriate primer, contact your local Stonhard representative or Technical Service.

**Note:** Stonclad UR is suitable for application over new/green concrete. The concrete must be in place for a minimum of 5 days, be dry and have sufficient strength to handle mechanical preparation.

## SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

## PRIMING

The use of Urethane Primer is necessary for all applications of Stonclad UR. See the Urethane Primer Product Data sheet for details.

## MIXING

- Proper mixing is critical for the product to exhibit the proper application properties, cure properties and ultimate physical properties.
- Mechanical mixing using a JB Blender (or equivalent 5 gal. pail mixer) or a larger mortar mixer (e.g., a Baugh 3 Batch Mixer) is required.
- See Stonclad UR Directions for further details.

## APPLYING

- DO NOT attempt to install material if the temperature of Stonclad UR components and substrate are not within 60 to 85°F/16 to 30°C. The cure time and application properties of the material are severely affected at temperatures outside of this range.
- Material must be applied immediately after mixing.
- A suitable screed applicator is used to distribute the mixed Stonclad UR onto the floor.
- Steel finishing trowels are used to compact and smooth the surface of the material to the required thickness.
- Detailed application instructions can be found in the Stonclad UR Directions.

## NOTES

- Procedures for maintenance of the flooring system during operations are described in the Stonkleen Floor Cleaning Procedures Brochure.
- Specific information regarding chemical resistance is available in the Stonclad Chemical Resistance Guide. If a coating is utilized to seal the Stonclad UR surface, please ensure that you consult the Product Data sheet for the coating for details regarding chemical resistance of the coating utilized.
- Safety Data Sheets for Stonclad UR are available on line at [www.stonhard.com](http://www.stonhard.com) under Tech Info or upon request.
- A staff of technical service engineers is available to answer questions related to Stonhard products specifically or flooring problems in general.
- Requests for literature can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, high gloss coatings are subject to a reduction in gloss, while matte finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant buildup occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction-enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

### IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Rev. 4/16  
© 2016 Stonhard



**STONHARD**<sup>®</sup>  
[www.stonhard.com](http://www.stonhard.com)



### Worldwide Offices:

USA 800.257.7953  
Canada (905)430.3333

Mexico (52)55.9140.4500  
South America (54-3327)44.2222

Europe (32)2.720.8982  
Middle East (971)4.3470460

Africa (27)11.254.5500  
Asia (86)21.5466.5118