

PRODUCT DESCRIPTION

Stongard MR is a nominal 30 to 40 mil/0.75 to 1 mm thick flooring system created for positive side waterproofing applications. It is designed to protect areas below mechanical rooms, pump and mezzanine floors. It is comprised of:

Stonproof ME7

A two-component, free-flowing, 100% solids, urethane, elastomeric waterproof membrane

Stonkote GS4

A two-component, 100% solids, general purpose, epoxy coating

OPTIONS

Cove Base

Provides an integral seal at the joint between the floor and the wall. Cove bases in heights from 2 to 6 in./5 to 15 cm are available.

PACKAGING

Stongard MR is packaged in units for easy handling. Each unit consists of:

Stonproof ME7

1 carton containing:
6 foil bags of Isocyanate

1 carton containing:
6 poly bags of Polyol

Stonkote GS4

0.75 cartons containing:
4 foil bags of Amine
4 poly bags of Resin

COVERAGE

Each unit of Stongard MR will cover approximately 300 sq. ft./27.9 sq. m of surface at a nominal 30 to 40 mil/0.75 to 1 mm.

STORAGE CONDITIONS

Store all components of Stongard MR between 60 to 85°F/16 to 30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life for epoxy primers/coatings is 3 years; the shelf life for Stonproof ME7 is 2 years in the original, unopened container.

COLOR

Stongard MR is available in 12 standard colors. Custom colors are available upon request.

PHYSICAL CHARACTERISTICS

Tensile Strength	1,200 psi (ASTM D-412)
Elongation200% (ASTM D-412)
Hardness70 (ASTM D-2240, Shore A)
Theoretical Coverage300 sq. ft./27.87 sq. m
Pot Life30 to 35 minutes (@ 77°F/25°C)
Abrasion Resistance	0.06 gm (ASTM D-4060, CS-17)
Water Absorption	0.1% (ASTM C-413)
VOC Content	Stonproof ME7 - 8 g/l (ASTM D-2369) Stonkote GS4 - 30 g/l
Cure Rate8 to 10 hours (@ 77°F/25°C) for tack-free surface 24 hours for normal operations

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab made test coupons.

SUBSTRATE

Stongard MR, in conjunction with the proper primers, is suitable for application over properly prepared concrete, metal or wood. For questions regarding other possible substrates or an appropriate primer; contact your local Stonhard representative or Technical Service.

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

PRIMING

The use of Standard Primer and SL Primer is necessary for all applications of Stongard MR over all substrates except Stonset grouts. Over Stonset grouts, Stonhard's Stonset Primer is used. Please see the appropriate primer Product Data sheet for details.

MIXING

- Proper mixing is critical for the product to exhibit the proper application properties, cure properties and ultimate physical properties.
- Mechanical mixing using a slow-speed drill and mixing blade.
- See Stongard MR Directions for further details.

APPLYING

- DO NOT attempt to install material if the temperature of Stongard MR components and substrate are not within 60 to 85°F/16 to 30°C. The cure time and application properties of the material are severely affected at temperatures outside of this range.
- Material must be applied immediately after mixing.
- Detailed application instructions can be found in the Stongard MR Directions.

NOTES

- Procedures for maintenance of the flooring system during operations are described in the Stonkleen Floor Cleaning Procedures Brochure.
- Specific information regarding chemical resistance is available in the Stonkote GS4 Product Data sheet.
- Safety Data Sheets for Stongard MR are available on line at www.stonhard.com under Products or upon request.
- A staff of technical service engineers is available to assist with installation or to answer questions related to Stonhard flooring products.
- Requests for technical service or literature can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, high gloss coatings are subject to a reduction in gloss, while matte finish coatings can increase in gloss level under normal operating conditions.

- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant buildup occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction-enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Rev. 4/16
© 2016 Stonhard



Worldwide Offices:

USA	800.257.7953	Mexico	(52)55.9140.4500	Europe	(32)2.720.8982	Africa	(27)11.254.5500
Canada	(905)430.3333	South America	(54-3327)44.2222	Middle East	(971)4.3470460	Asia	(86)21.5466.5118



STONHARD[®]
www.stonhard.com