

PRODUCT DESCRIPTION

Stontec TRF is a nominal 3/16 in./5 mm thick durable floor system with a decorative, stain resistant surface. It's troweled base provides superior impact resistance and allows Stontec TRF to be applied over rough substrates. The color flake broadcast layer results in an attractive, seamless floor surface. It is comprised of:

Urethane Mortar

A four component, troweled high solids urethane mortar system that is applied at an 1/8 in./3 mm.

TRF Undercoat

A two-component, high solids, epoxy bonding coat. A colored coat that accepts the flakes.

Stontec Flakes

Brightly colored flakes

Stonseal CA7

A two-component, UV resistant, aliphatic polyaspartic urethane sealer

SYSTEM OPTIONS

Waterproofing

Where the total system must be waterproof, use of Stonhard's Stonproof ME7 membrane system with texture #3 Broadcast to refusal is required, with strict adherence to application instructions.

Cove Base

To provide for an integral seal at the joint between the floor and the wall, cove bases in heights from 2 to 6 in./5 to 15 cm may be specified.

PACKAGING

Stontec TRF is packaged in units for easy handling.

Each unit consists of:

Urethane Mortar

- 1.5 cartons containing:
 - 6 foil bags of Isocyanate
 - 6 poly bags of Polyol

9 individual bags of Part C-1 aggregate

0.75 carton of Part C-2 pigment

TRF Undercoat

- 0.5 carton containing:
 - 4 foil bags of Amine
 - 4 poly bags of Resin

PHYSICAL CHARACTERISTICS

Tensile Strength	1,000 psi
(ASTM D-638)	
Impact Resistance	>160 in./lbs.
(ASTM D-4226)	
Abrasion Resistance	<.03 gm max
(ASTM D-4060, CS-17)	
Cure Rate4 hours for foot traffic
(@ 77°F/25°C)	12 hours for normal operations
Flexural Strength2,000 psi
(ASTM C-580)	
Flexural Modulus of Elasticity	1.1x10 ⁶ psi
(ASTM D-790)	
Hardness80
(ASTM D-2240, Shore D)	
Flammability	Class 1
(ASTM E-648)	
Linear Coefficient of Thermal Expansion	12x10 ⁻⁶ in./in. °F
(ASTM C-531)	
Compressive Strength5,000 psi
(ASTM C-579)	after 7 days
VOC Content	Urethane Mortar - 5 g/l
(ASTM D-2369, Method E)	TRF Undercoat - 30 g/l
	Stonseal CA7 - 100 g/l

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab made test coupons.

Stontec Flakes

- 0.67 individual boxes of small (1/16 in.) colored flakes or
- 0.50 individual boxes of large (1/4 in.) colored flakes

Stonseal CA7

- 1 carton containing:
 - 2 foil bags of Isocyanate
 - (2)1 gallon cans of a Amine

IMPORTANT: Appropriate Primer must be ordered separately depending on the substrate.

COVERAGE

Each unit of Stontec TRF will cover approximately 200 sq. ft./18.6 sq. m of surface at a nominal 3/16 in./5 mm thickness.

STORAGE CONDITIONS

Store all components of Stontec TRF between 60 to 85°F/16 to 30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life is 2 years for urethane mortar, 3 years for TRF Undercoat and one year for Stonseal CA7.

COLOR

Stontec TRF is available in twelve standard colors in small (1/16 in.) or large (1/4 in.) sized flakes. Refer to the Stontec Color Sheet. Custom colors are available upon request.

Note: Micro (1/32 in.) flakes are available upon special request.

SUBSTRATE

Stontec TRF, with the appropriate primer, is suitable for application over properly prepared concrete, wood, brick, quarry tile, metal or Stonhard Stonset grouts. For questions regarding other possible substrates or an appropriate primer, contact your local Stonhard representative or Technical Service.

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

PRIMING

The use of Urethane Primer is necessary for all applications of Stontec TRF. The Urethane Primer must be tacky during the application of the Stontec TRF Mortar. If the primer becomes tack-free, the area must be re-primed prior to continuing the application.

MIXING

- Proper mixing is critical for the products to exhibit the proper application properties, cure properties and ultimate physical properties.
- Mechanical mixing is required for all components.
- See Stontec TRF Directions for further details.

APPLYING

- DO NOT attempt to install material if the temperatures of Stontec TRF components are not within 60 to 85°F/16 to 30°C. The cure time and application properties of the material are affected by temperature and severely affected by humidity levels.
- The primer is applied to the floor and the mortar is immediately troweled into the wet primer and allowed to cure.
- The undercoat is mixed, applied to the floor and broadcasted to refusal with Stontec Flakes. The undercoat is allowed to cure and excess flake is removed.

- The sealer is mixed, applied to the floor and allowed to cure. The sealer is lightly sanded and vacuumed.
- A second sealer is applied in the same manner as the first and allowed to cure.

Refer to the Stontec TRF Directions for further detail.

NOTES

- Procedures for maintenance of the flooring system during operations are described in the Stonkleen Floor Cleaning Procedures Brochure.
- Specific information regarding chemical resistance is available in the Stontec Chemical Resistance Guide.
- Safety Data Sheets for Stontec TRF are available on line at www.stonhard.com under Products or upon request.
- A NIOSH approved air purifying respirator (APR) equipped with organic vapor/acid gas cartridges is required during application of the Stonseal CA7.
- A staff of technical service engineers is available to assist with installation or to answer questions related to Stonhard flooring products.
- Requests for technical service or literature can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, high gloss coatings are subject to a reduction in gloss, while matte finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant buildup occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction-enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Rev. 04/16
© 2016 Stonhard



STONHARD[®]
www.stonhard.com



Worldwide Offices:

USA	800.257.7953	Mexico	(52)55.9140.4500	Europe	(32)2.720.8982	Africa	(27)11.254.5500
Canada	(905)430.3333	South America	(54-3327)44.2222	Middle East	(971)4.3470460	Asia	(86)21.5466.5118